

### TECHNICAL DATA SHEET

## UMITAN RS / CU LIQ.

# RESIN RETANNING CHEMICAL COMPOSITION

High molecular plastic polymer chemically modified to make it polar

#### **FEATURES**

Appearance: clear liquid pink

pH in solution at 10%: 5 - 6
Ionic charge: anionic

Solubility: in water complete

Concentration: 10–15%

Compatibility: natural with synthetic tannins with

polyacrylates sulphonated oils sulfitated

Storage: 6 months in normal conditions

### **PROPERTY**

UMITAN RS / CU LIQ. Can be used alone or in combination with natural and synthetic tannins, which are added to the same bath. UMITAN RS / CU imparts to leather grain firmness and exceptional fullness and roundness of hand.

The percentages of use are from 3 to 6% on the weight of the hides shaved, depending on the type of leather and of their thickness. It is also used at the end after the fattening for maximum effect.

DATA AND NEWS HAVE VALUES