### TECHNICAL DATA SHEET

## UMITAN TA / FAB POLV.

# TANNINO SYNTHETIC CHEMICAL COMPOSITION

Riconiante based dihydroxy - diphenyl-sulfone

### **FEATURES**

Appearance: white powder

pH in solution at 10%: 3.5 - 4.5

active substance: approximately 90%

### **PROPERTY**

Used in the chrome tanning, the **UMITAN TA / FAB** pow produces leather with a touch soft and round with firm grain, this makes it particularly suitable for the retanning of soft leathers such as shoe nappa, nappa clothing, etc...

Is recommended for use from 2% to 8%, depending on the skin type and the degree of softness desired. UMITAN TA / FAB is also particularly suitable for the tanning of leather for car upholstery and soft furnishings for living rooms. Possessing a good bleaching power, it is suitable for tanning materials for light colors and pastels. UMITAN TA / FAB can be used in retanning in combination with tanning agents and resins, producing excellent fullness and roundness, for both full-grain leathers, pure aniline for corrected grain, in this case it is recommended the use of 2% - 4%. UMITAN TA / FAB could be used as perconciante before the chrome tanning of rams, improving the fullness in the emptiest areas of the skin. For this application we recommend the use of 3% -5% based on the weight pickled.