



INTISO chemicals

di Intiso Pietro Livio

TECHNICAL DATA SHEET

UMITAN TA / SB POLV.

SYNTHETIC TANNIN

CHEMICAL COMPOSITION

Product based on dihydroxy-diphenyl-sulfone

FEATURES

Appearance: c lear powder
pH in solution at 10%: 3.5 - 4.5

PROPERTY

UMITAN TA / SB pol is used both in tanning and retanning for the production of all types of white leather, alone or in combination of natural tannins. It can be used also in the retanning of chrome, after neutralization, or bleaching of vegetable leathers.

HOW TO USE

12-15% on shaved weight for the retanning of chrome leather for white.

3-5% on shaved weight, mixed with vegetable tannins, for the retanning of chrome leather.

8-10% on shaved weight for a comeback clear of vegetable tanned leathers.

DATA AND NEWS HAVE VALUES